



## TECHNICAL DATA SHEET - DIGITAL PRINTING - PVC - PERMANENT ADHESIVE V200WGI

Film composed of a 70- $\mu$ m calendered, polymeric PVC, which is coated with a grey pressure-sensitive acrylic adhesive. For solvent, eco-solvent, latex and UV inkjet printing. Glossy surface finish.

### FILM FEATURES:

	<u>Indicative values</u>	
• Thickness ( $\mu$ m):	70	
• Total thickness of the product ( $\mu$ m):	260	
	<u>Average values</u>	<u>Standard</u>
• Total weight of the product ( $\text{g}/\text{m}^2$ ):	280	HEXGSM001
• Tensile strength (N/25 mm):	min. 35	HEXNFX41021
• Elongation at break (%):	min. 100	HEXNFX41021
• Shrinkage 168 hours at 70 °C (158 °F) (mm):	< 0.4	HEXRET001

### GENERAL PRINTER COMPATIBILITES:

	<b>Solvent</b>	<b>Eco-solvent</b>	<b>Latex</b>	<b>UV</b>
<b>V200WGI</b>	✓	✓	✓	✓

### LINER:

- Silicone-coated PE paper 145  $\text{g}/\text{m}^2$  with light grey HEXIS print.
- Stable under hygrometric variations.

### ADHESIVE PROPERTIES:

(Measured average values at publication of the technical data sheet)

	<u>Average values</u>	<u>Standard</u>
• Peel strength test 180° on glass (N/25 mm):		HEXFTM001
after 20 minutes of application	16	
after 24 hours of application	18	
• Initial tack (N/25 mm):	14	HEXFTM009
• Release (N/25 mm):	0.3	HEXFTM003
• Resistance to solvents: the adhesive is resistant to most chemicals (alcohol, diluted acids, oils).		

**ADHESIVE:**

- Solvent-based grey acrylic adhesive.
- Immediate and permanent adhesion.

**USER'S INSTRUCTIONS:**

- Touch-dry after less than 10 minutes depending on printer used.
- Recommended minimum application temperature: +10 °C (+50 °F).
- Operating temperature range (outdoors): from -40 °C to +90 °C (-40 °F to +194 °F).
- Very good adhesion to glass, steel, aluminium, PVC, melamine, etc. except grain substrates or substrates coated with acrylic paint.
- In the case of already painted substrate, self-adhesive media must only be applied to undamaged original paintwork. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.

**OPERATING RECOMMENDATIONS:**

- For any coating and other, optimal drying time for the inks is 24 hours minimum.
- The surface finish of your printing may be modified/improved/protected by a judicious choice of laminating films V750 or PC500. For UV printing, protect with the VCR750 laminate.
- For more information on the application method of V200WGI, please refer to its Application Guide on the "Professionals" pages, category "Digital printing media" on our website [www.hexis-graphics.com](http://www.hexis-graphics.com).

**STORAGE:**

- Shelf life (before application):

The shelf life of this film is 1 year when stored unopened in its original packaging at a temperature ranging from +15 °C to +25 °C (+59 °F to +77 °F) with relative humidity between 30 % and 70 %.

**DURABILITY:** (Central Europe Climate)

- Vertical outdoor exposure:  
Unprinted: 8 years.  
Printed and laminated:  
- PC500: 5 years.  
- V750: 4 years.  
- VCR750: 3 years.  
Printed: 2 years.

**NOTES:**

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the media for each application. The measuring methods for the standards quoted above served as basis for the development of our own measuring methods which are available on request. Please feel free to contact us to get the latest instructions in use.

All the published information is based on measurements regularly performed in the laboratory. It does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website [www.hexis-graphics.com](http://www.hexis-graphics.com).